

LANKA WALLTILES PLC

215, Nawala Road, Narahenpita, Colombo 05, Sri Lanka.Tel:
+94-11-2808050 Fax: +94-11-2806232
Email: info@lankatiles.com Website: www.lankatiles.com
Factory: Meepe, Padukka. Tel: 0117309804-9
Fax:0112859168
Co. Reg. No. PQ55



TECHNICAL SPECIFICATION



Glazed Ceramic Floor Tiles produced by LANKA TILES PLC comply with ISO 13006:2018(E) Annex J, BS EN 14411:2012 Annex J, SLS 1181:2019 standards.

SKU: FAP-WES---X0884C6

Series : Warm waves

Tile Size: 300x600mm

Tile Surface: Rough Matt

DIMENSIONS & SURFACE QUALITY	IMAGE	Test methods BS EN ISO	GLAZE CERAMIC Annex J Group B11a	TEST STATUS
Length & width		ISO 10545-2	+/-0.3%	Comply
Thickness		ISO 10545-2	+/-5.0%	
Straightness of sides		ISO 10545-2	+/-0.3%	
Centre curvature		ISO 10545-2	+/-0.4%	
Edge curvature		ISO 10545-2	+/-0.4%	
Warpage		ISO 10545-2	+/-0.4%	
Rectangularity		ISO 10545-2	+/-0.3%	
Surface quality		ISO 10545-2	Minimum of 95 % of tiles shall be free from visible defects that would impair the appearance of a major area of tiles.	
PHYSICAL PROPERTIES				
Water absorption		ISO 10545-3	3 % < E ≤ 6 % Individual max 6.5%	Comply
Breaking strength		ISO 10545-4	Not less than 1000 N (Thickness ≥ 7.5mm)	
Modulus of rupture		ISO 10545-4	Min 22 N/ mm ² Individual min 20 N/mm ²	
Resistance to surface abrasion-glazed tiles		ISO 10545-7	Reported abrasion class and cycle passed	Class 3
Scratch Resistance (Mohs Hardness Scale)		NA	Not Specified	6
Resistance to Slip		BS 7976 / EN 16165	Reported Slippery class	P3/R10
Resistance to Thermal shock		ISO 10545-9	Required	Comply
Resistance to crazing-glazed tiles		ISO 10545-11	Required	
CHEMICAL PROPERTIES				
Resistance to staining		ISO 10545-14	Minimum class 3	Class 5
Resistance to low concentrations of acids		ISO 10545-13	Manufacturer to state classification	Class GLA
Resistance to low concentrations of alkalis		ISO 10545-13	Manufacturer to state classification	Class GLA
Resistance to household chemicals and swimming pool salts		ISO 10545-13	Minimum GB	GA
APPLICATIONS		Recommended for industrial, residential, or medium traffic commercial floor covering areas (indoor/outdoor) subject to normal footwear. Ex- Office area except for entrances, Kitchens, Corridors and balconies, and Laboratories which do not require strong acid resistance. Cleaning ability to be considered.		

Last Update: 2026-03-17

Prepared By: Executive (QA)

Approved By : Manager (QA/RD)

Signature

Signature