

LANKA WALLTILES PLC

215, Nawala Road, Narahenpita, Colombo 05, Sri Lanka.Tel:
+94-11-2808050 Fax: +94-11-2806232
Email: info@lankatiles.com Website: www.lankatiles.com
Factory: Meepe, Padukka. Tel: 0117309804-9
Fax:0112859168
Co. Reg. No. PQ55



TECHNICAL SPECIFICATION

Glazed Porcelain Floor Tiles produced by LANKA WALLTILES PLC comply with ISO 13006:2018(E) Annex H, BS EN 14411:2012 Annex H, Specifications and SLS 1181:2019 standards.

SKU : FAZ-WOL---U0940A6

Series : Woodland

Size: 1000x1000mm

Surface: Rough Matte

DIMENSIONS & SURFACE QUALITY	IMAGE	Test methods BS EN ISO	GLAZE PORCELAIN Annex H Group B I b	TEST STATUS
Length & width		ISO 10545-2	+/-0.3%	Comply
Thickness		ISO 10545-2	+/-5.0%	
Straightness of sides		ISO 10545-2	+/-0.3%	
Centre curvature		ISO 10545-2	+/-0.4%	
Edge curvature		ISO 10545-2	+/-0.4%	
Warpage		ISO 10545-2	+/-0.4%	
Rectangularity		ISO 10545-2	+/-0.3%	
Surface quality		ISO 10545-2	Minimum of 95 % of tiles shall be free from visible defects that would impair the appearance of a major area of tiles.	
PHYSICAL PROPERTIES				
Water absorption		ISO 10545-3	0.5 % < E ≤ 3 % Individual Max 3.3%	Comply
Breaking strength		ISO 10545-4	Not less than 1100 N (Thickness ≥ 7.5mm)	
Modulus of rupture		ISO 10545-4	Min 30 N/ mm² Individual min 27 N/mm²	
Resistance to surface abrasion-glazed tiles		ISO 10545-7	Reported abrasion class and cycle passed	Class 3
Resistance to Slip		BS 7976 / EN 16165	Reported Slippery class	P3
Scratch Resistance (Mohs Hardness Scale)		NA	Not Specified	6
Resistance to Thermal shock		ISO 10545-9	Required	Comply
Resistance to crazing-glazed tiles		ISO 10545-11	Required	
CHEMICAL PROPERTIES				
Resistance to staining		ISO 10545-14	Minimum class 3	Class 5
Resistance to low concentrations of acids		ISO 10545-13	Manufacturer to state classification	Class GLA
Resistance to low concentrations of alkalis		ISO 10545-13	Manufacturer to state classification	Class GLA
Resistance to household chemicals and swimming pool salts		ISO 10545-13	Minimum GB	GA
APPLICATIONS		Recommend residential or medium-traffic commercial floor covering areas (indoor) suitable for normal footwear. Ex-Office areas, except entrances, Kitchens, Laboratories, which do not require strong acid resistance		